

MOTIVE T1275-AGM

MODEL T1275-AGM

VOLTAGE 12

CAPACITY 132Ah @ 20Hr MATERIAL Polypropylene

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required









12 VOLT

PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	TERMINAL TYPE G	DIMENSIONS © INCHES (mm)		WEIGHT LBS. (kg)	HANDLES	INSTALLATION ORIENTATION			
2010			LENGTH	WIDTH				Horizontal		
GC12	T1275-AGM	M8/AP/LT	12.96 (329)	7.06 (179)	10.96 (278)	83 (38)	83 (38)	83 (38)	Embedded	and Vertical

ELECTRICAL SPECIFICATIONS

VOLTAGE	Cranking P	erformance	Capacity	^A Minutes	CAPACITY ^B AMP-HOURS (Ah)		ENERGY (kWh)	INTERNAL RESISTANCE (m Ω)	SHORT CIRCUIT CURRENT (amps)		
10	C.C.A. ^D @0°F	C.A. ^E @32°F	@ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	4.2	2920
12	_	_	254	70	114	126	132	135	1.62	4.3	

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
SYSTEM VOLTAGE	12V	24V	36V	48V	
Maximum Charge Current (A)	20% of C ₂₀				
Absorption Voltage (2.40 V/cell)	14.40	28.80	43.20	57.60	
Float Voltage (2.25 V/cell)	13.50	27.00	40.50	54.00	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F

OPERATIONAL DATA

OPERATING TEMPERATURE	SELF DISCHARGE		
-4°F to 122°F (-20°C to 50°C) At temperatures below 32°F (0°C) maintain a state of charge greater than 60%	Less than 3% per month depending on storage temperature conditions		

RECYCLE RESPONSIBLY









STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	CELL	12 VOLT
100	2.14	12.84
75	2.09	12.54
50	2.04	12.24
25	1.99	11.94
0	1.94	11.64


TROJAN T125-AGM PERFORMANCE





PERCENT CAPACITY VS. TEMPERATURE




BATTERY DIMENSIONS (shown with M8)








SELF DISCHARGE VS. TIME



TERMINAL CONFIGURATIONS⁶



M8 M8 WITH AP ADAPTER (ADAPTER PROVIDED BUT NOT INSTALLED) **Battery Height with Terminal in Inches (mm)** 11.41 (290) Torque Values in-lb (Nm) Connection to M8: 85 - 90 (10 - 11)Connection to AP: 50 - 70 (6 - 8)

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are
- The anount of aminists a studied year learner when discharged at a constant rate at 60° (27°) and maintain a studieg above 1.73 Vicen. Capacities based on peak performance.

 The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80° (27°C) for the 20-Hour rate and 66°F (30°C) for the 5-Hour rate and maintain a voltage above 1.75 Vicen. Capacities are based on peak performance.

 Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.
- C.C.A. (Cold Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2
- CAL Clothaning Arrips: The deschage lower in amperes which a reve, may view got battery 2 and maintain to 30 seconds at 32 V/Cell. This is sometimes referred to as marine cranting amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.
- A boost charge should be performed every 6 months when batteries are in storage.
- Weight may vary.











Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

